

RUBADUEWIRE

Reinforced (3 layers) Insulation FEP .005" / Layer

Product Information

Temperature Rating: 155°C

Insulation: DuPont™ Teflon® FEP

Compliances: UL OBJT2 File No. E206198

UL/IEC 60950-1 (Ed.2) Annex U

IEC 61010-1 (Ed.2)

VDE License Nr. 6715: Class F

System approvals: UL 1446

RXT-2 Class F, TCA Class F

RoHS Compliant

Conductor: Tin plated copper, solid or stranded (ASTM B-33/ASTM B-286)
Bare copper and other conductors available

Size Range: 10 AWG – 28 AWG

Voltage: 1000 V

Breakdown: Approx. 15000 V

OD Tolerances: 10- 28 AWG + 0.003"/-0.002"

Insulation Information:

Insulation Type: Fluoropolymer

Dielectric Constant: 2.03

Abrasion Resistance: Good

Chemical Resistance: Excellent

Underground Resistance: Excellent

Thermal: Continuous Operating Temperature, 200°C

Tensile Strength (psi): 3000+

Bondability: Poor

Water Resistance: Excellent

Long Term Stability: Excellent

UL Flammability Rating: V-0

Elongation (%): 300

UV Resistance: Excellent

FEP is a Fluoropolymer compound with exceptional dielectric properties, heat resistance, chemical resistance, and flexibility. Commonly used in winding wires, UL AWM wires, and cable jacketing.

Insulated Wire Information:

Part Number	AWG	Conductor OD		Insulated Wire OD		Weight LB/KFT
		Inches	MM	Inches	MM	
T10A37FXXX-5	10(37/26)	0.1070	2.718	0.1370	3.480	34.37
T12A19FXXX-5	12(19/25)	0.0862	2.189	0.1162	2.951	23.35
T14A19FXXX-5	14(19/27)	0.0679	1.725	0.0979	2.487	15.53
T16A01FXXX-5	16	0.0508	1.290	0.0808	2.052	10.77
T16A19FXXX-5	16(19/29)	0.0539	1.369	0.0839	2.131	10.59
T18A01FXXX-5	18	0.0403	1.024	0.0703	1.786	7.41
T18A19FXXX-5	18(19/30)	0.0476	1.209	0.0776	1.971	8.69
T20A01FXXX-5	20	0.0320	0.813	0.0620	1.575	5.21
T20A19FXXX-5	20(19/32)	0.0385	0.978	0.0685	1.740	6.16
T22A01FXXX-5	22	0.0253	0.643	0.0553	1.405	3.75
T22A19FXXX-5	22(19/34)	0.0295	0.749	0.0595	1.511	4.33
T24A01FXXX-5	24	0.0201	0.511	0.0501	1.273	2.80
T24A19FXXX-5	24(19/36)	0.0242	0.615	0.0542	1.377	3.23
T26A01FXXX-5	26	0.0159	0.404	0.0459	1.166	2.16
T26A19FXXX-5	26(19/38)	0.0190	0.483	0.0490	1.245	2.42
T28A01FXXX-5	28	0.0126	0.320	0.0426	1.082	1.72
T28A19FXXX-5	28(19/40)	0.0152	0.386	0.0452	1.148	1.93

Bare Core Wire Specifications:

DCR per 10' @ 20°C

AWG	Core Wire Diameter			DC Resistance		
	Min. Dia.	Nom. Dia.	Max. Dia.	Min. Res.*	Nom. Res.	Max. Res.
10	0.1009	0.1019	0.1050	0.0096	0.0104	0.0109
11	0.0898	0.0907	0.0934	0.0122	0.0131	0.0138
12	0.0800	0.0808	0.0832	0.0153	0.0165	0.0174
13	0.0713	0.0720	0.0742	0.0193	0.0208	0.0219
14	0.0635	0.0641	0.0660	0.0244	0.0262	0.0276
15	0.0565	0.0571	0.0588	0.0307	0.0331	0.0349
16	0.0503	0.0508	0.0523	0.0388	0.0418	0.0440
17	0.0448	0.0453	0.0467	0.0487	0.0526	0.0555
18	0.0399	0.0403	0.0415	0.0617	0.0664	0.0699
19	0.0355	0.0359	0.0370	0.0776	0.0837	0.0883
20	0.0317	0.0320	0.0330	0.0975	0.1053	0.1108
21	0.0282	0.0285	0.0294	0.1229	0.1328	0.1400
22	0.0250	0.0253	0.0261	0.1559	0.1685	0.1781
23	0.0224	0.0226	0.0233	0.1956	0.2112	0.2219
24	0.0199	0.0201	0.0207	0.2478	0.2669	0.2811
25	0.0177	0.0179	0.0184	0.3137	0.3366	0.3554
26	0.0157	0.0159	0.0164	0.3948	0.4266	0.4517
27	0.0141	0.0142	0.0146	0.4982	0.5349	0.5600
28	0.0125	0.0126	0.0130	0.6283	0.6793	0.7125

*ASTM B33 sets no standard for minimum resistance. This is only an indicator to investigate other aspects such as tin-thickness and tin coverage.